



Contact Washers with Barbs





English	Français	Deutsch	Italiano	Español
Steel C60S to C75S	Acier C60S à C75S	Stahl C60S bis C75S	Acciaio C60S a C75S	Acero C60S a C75S
Zinc plated	Zingué	Verzinkt	Zincato	Zincado
Clear passivated 5µ	Passivé clair 5µ	Klar chromatiert 5µ	Bianco 5µ	Pasivado Claro 5µ
<i>Stainless steel on special request</i>	<i>Inox sur demande</i>	<i>Edelstahl auf Anfrage</i>	<i>acciaio inossidabile a richiesta</i>	<i>Acero inoxidable bajo pedido</i>
Hardness: 420 to 510 Hv	Dureté: 420 à 510 Hv	Härte: 420 bis 510 Hv	Durezza: 420 a 510 Hv	Dureza: 420 a 510 Hv

*: to red rust / à la rouille rouge / bis Rotrost / alla ruggine rossa / al óxido rojo



72 h*




screw / vis / Schraube / vite / tornillo Ø	Ø d1	Ø d2	e	No. of splines / dents / Rippen / scanalature / estrías min.	No. of barbes / picots / Kontakt- punkte / tacchetti / estrías 6	Height of barbs/ hauteur de picots / Höhe der Kontaktpunkte/ altezza dei tac- chetti / altura de las estrías		Part No/ref	
						min.	max.		
3	3.1 +0.30	6.0 ±0.24	0.6 ±0.03	28	6	0.20	0.80	0.95	55 03 03
4	4.1 +0.30	8.0 ±0.29	0.8 ±0.03	35			1.00	1.15	55 04 03
5	5.1 +0.30	10.0 ±0.29	1.0 ±0.04	35		0.30	1.25	1.50	55 05 03
6	6.1 +0.36	12.0 ±0.35	1.2 ±0.04	45			1.50	1.80	55 06 03
6	6.1 +0.36	18.0 ±0.35	1.4 ±0.04	45			2.25	2.55	55 06 17
6 ¹⁾	6.45 +0.36	14.0 ±0.35	1.4 ±0.04	45			1.90	2.20	55 06 37
8	8.2 +0.36	14.0 ±0.35	1.4 ±0.04	45			1.70	2.00	55 08 24
8	8.2 +0.36	16.0 ±0.35	1.4 ±0.04	45			1.95	2.40	55 08 25
10	10.2 +0.43	20.0 ±0.42	1.6 ±0.05	45			2.15	2.60	55 10 25
12	12.4 +0.43	24.0 ±0.42	1.6 ±0.05	45			2.15	2.60	55 12 43

all dimensions in mm / en millimètres / alle Maße in mm / in millimetri / en milímetros

1) for 1/4" screws / pour vis 1/4" / für 1/4" Schrauben / per viti 1/4" / para tornillos de 1/4"

Finishes / finition / Oberflächen / superficie / superficie

Type	Description / description / Beschreibung / descrizione / descripción	Cr6	 2)	Code ³⁾
Standard	Zinc clear passivated 5 µ / Zingué passivé clair 5µ / Verzinkt, klar chromatiert 5µ / Zincato bianco 5µ / Zincado y pasivado claro 5µ	✓	72 h	32
Optional	Unfinished, lubricated / Brut, huilé / Blank, mit Gleitmittel / Nessuna finitura e lubrificazione / Acabado natural y engrasado	✓	-	00
Optional	Zinc clear passivated 8 µ / Zingué passivé clair 8 µ / Verzinkt, klar chromatiert 8 µ / Zincato bianco 8 µ / Zincado y pasivado claro 8 µ	✓	400 h	31
Optional	Zinc clear passivated 10 µ / Zingué passivé clair 10 µ / Verzinkt, klar chromatiert 10 µ / Zincato bianco 10 µ / Zincado a pasivado claro 10 µ	✓	600 h	78
Optional	Dacromet® 500 A	-	500 h	37

2) to red rust / à la rouille rouge / bis Rotrost / alla ruggine rossa / al óxido rojo

3) add code to part number / ajoutez le code à la référence / fügen Sie den Code zur Artikel-Nummer hinzu / aggiungere il codice al numero di codice / añadir numeración a la referencia



www.acument.com

© 2008 Acument Intellectual Properties, LLC

Dacromet® is a trademark of Metal Coatings International, Inc.

Data shown is subject to change without prior notice as a result of continuous product development and improvement policy. Your local Acument Global Technologies representative is at your disposal should you need to confirm latest information.